

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
11 January 2001 (11.01.2001)

PCT

(10) International Publication Number
WO 01/02475 A1

- (51) International Patent Classification⁷: C08K 9/08, (81) Designated States (*national*): AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZA, ZW.
- C09C 3/10, C08L 23/02, C08J 5/18
- (21) International Application Number: PCT/IB99/02099
- (22) International Filing Date:
22 December 1999 (22.12.1999)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
09/343,825 30 June 1999 (30.06.1999) US
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- (71) Applicant: MINERALS TECHNOLOGIES INC.
[US/US]; The Chrysler Building, 405 Lexington Avenue,
New York, NY 10174 (US).
- Published:
— With international search report.

- (72) Inventor: DRUMMOND, Donald, Kendall; 1715 Canary Road, Quakertown, PA 18951 (US).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 01/02475 A1

BEST AVAILABLE COPY

(54) Title: ANTIBLOCK COMPOSITIONS AND METHOD OF PREPARATION

(57) Abstract: The present invention relates to a product, a process for its preparation and the use of such in plastic film production. More specifically, the present invention relates to an antiblock talc, a process for the preparation of such and its use as an additive in the production of polyolefin film. Polyolefin films produced according to the process of the present invention are useful in a broad range of packaging and film covering applications.

ANTIBLOCK COMPOSITIONS AND METHOD OF PREPARATIONFIELD OF THE INVENTION

5 The present invention relates to a product, a process for its preparation and the use of such in plastic film production. More specifically, the present invention relates to an antiblock talc, a process for the preparation of such and its use as an additive in the production of polyolefin film.

10 Polyolefin films produced according to the process of the present invention are useful in a broad range of packaging and film covering applications.

BACKGROUND OF THE INVENTION

15 Polyolefin films are used extensively for packaging and in film covering applications. The use of polyolefin films continues to increase as new market opportunities become available in areas where paper was traditionally used. The versatility of the film provides potentially infinite growth prospects for the product in the future. However, there is an inherent short coming in the use of plastic films that may retard its market acceptance and growth, it sticks. When
20 plastic film is produced or used in various applications, there is a tendency for contacting layers of the film to stick together or "block", making separation of the film, opening of bags made from the film, or finding the end of the film on plastic rolls difficult. The present invention relates to polyolefin resin compositions that are specifically designed to have satisfactory antiblocking capability.

25 Antiblock agents are materials that are added to polyolefin resins to roughen their surface and thereby prevent layers of the plastic film from sticking, hence the term, "antiblocking agent" is applied to such materials. Although, inorganic minerals, such as, for example, diatomaceous earth, synthetic silica and talc are known to reduce blocking when
30 added to polyolefin film resin compositions, each has both advantages and critical disadvantages.

 One comparative advantage of diatomaceous earth is that it is known to be a moderately effective antiblocking agent, when used as an antiblocking agent. However, it is
35 also known that diatomaceous earth adversely affects the film's physical properties, such as film clarity, film haze, and is very abrasive and moderately expensive and may pose a serious

health threat. Synthetic silicates are known to be effective as an antiblock, however a significant disadvantage of silica is that it is very expensive. Talc, on the other hand, has found increasing use as an effective antiblock agent over diatomaceous earth and synthetic silica because of a significant cost advantage over both. However, one major disadvantage when talc is added to polyolefin film resins, is that it aggressively adsorbs other film additives, such as antioxidants, slip agents and processing aid. The absence, or reduced level of these additives in polyolefin resin compositions during production, routinely cause processing problems and raise serious film quality concerns.

For example, antioxidants are added to improve film stability, slip agents are present in the resin to improve film converting, while processing aids are employed to improve film quality, and to provide lubrication during film extrusion by eliminating melt fracture. Melt fracture is a measure of film surface uniformity, appearance and strength. Of the three additives mentioned here, processing aids are most adversely affected by the presence of antiblock agents.

Although it is well known that all antiblock agents adsorb processing aids, talc antiblock agents adsorb greater levels of processing aids than either diatomaceous earth or synthetic silica antiblocks. Consequently, when resin compositions are produced having additives that include antiblock talc, it is necessary to increase the dosage of processing aids. The increased dosage adversely effects the over all production economics of the plastic film.

Therefore, what is needed is a new generation of talc antiblock agents that adsorb less process aids than either synthetic silica or diatomaceous earth.

RELATED ART

U.S. Pat. No. 5, 401, 482, discloses a method for the manufacture of a talc substance consisting of particles having a sheet structure, each particle having an internal crystalline structure and at least one hydrophilic surface, the method comprising heating talc particles to a temperature below 900 degrees Centigrade under conditions such as to avoid conversion of the talc into enstatite and in order to effect a surface modification consisting of substituting inert siloxane groups by active silanols.

U.S. Pat. No. 5,229,094 discloses a talc substance consisting of particles having a sheet structure, each particle comprising internal hydrophobic sheets, having the crystalline structure of talc within each unit and bonded together by cohesion forces typical of talc (Van der Waals forces), the talc substance being characterized in that each particle has at least one hydrophilic

SUMMARY OF THE INVENTION

5

A product and a method for producing an antiblock agent comprising surface treating an inorganic mineral with a functionalized siloxane polymer or a polyether polymer or functionalized polyether polymer or carbon based polymer. When inorganic minerals are coated with a functionalized siloxane polymer or a polyether polymer or a functionalized polyether polymer or carbon based polymer and subsequently used as an additive in the production of polyolefin film, the adsorption of other resin additives is substantially reduced.

10

15

Polyolefin films produced according to the process of the present invention are useful in a broad range of packaging and film covering applications.

DETAIL DESCRIPTION OF THE INVENTION

20

In one aspect the present invention embodies surface treating talc with certain types of silanes or siloxane polymers. The treated talc inhibits the adsorption of plastic film additives onto the talc. Surface treating means coating, partially coating, or using an effective amount to inhibit the adsorption of other additives. The invention embodies of coating any talc material with a functionalized polydialkyl, preferably polydimethylsiloxane, having the structural formula:

25



where n is the number of repeating units (molecular weight), CH₃ is a methyl group, Si is silicon, O is oxygen, and R is a functionalized alkyl group. The alkyl group may, without limitation, be functionalized with carboxylate, amine, amide, thiol, sulfate, phosphate, and the like.

30

35


Siloxane polymers that are useful in the present invention may be selected from the group consisting of functionalized alkyl polydimethylsiloxane (carboxylate, amine, amide, thiol, sulfate, phosphate) wherein carboxylate is preferred, Bis-(12-hydroxystearate) terminated polydimethylsiloxane (Aldrich Chemical Co. – 1001 West Saint Paul Avenue, Milwaukee, WI 53233), and Poly(Dimethylsiloxane)-Graft-Polyacrylates (Aldrich). There is no limitation on the method used to produce the siloxane polymers. The siloxane polymers of the present invention may be manufactured by ionic polymerization or radical polymerization and the like, or any

other process known to produce siloxane polymers.

The molecular weight range of the siloxane polymer is from about 1000 to about 1,000,000 atomic mass units (a.m.u.), preferably ranges from about 1000 to about 100,000 a.m.u. The molecular weight can be determined by gel permeation chromatography (GPC).

Silanes that are useful in the present invention have the structural formula SiR_4 , where Si is silicon, R can be any group capable of forming a covalent bond with silicon (e.g., an alkyl group, an alkoxy group, a functionalized alkyl group, and a functionalized alkoxy group, and any combination thereof). The following silanes are useful in the present invention: Octyltriethoxysilane (OSi Silquest® A-137 silane), Triamino functional silane (OSi Silquest® A-1130 silane), Bis-(gamma-trimethoxysilylpropyl) amine (OSi Silquest® A-1170 silane), all of which are commercially available from OSi.

In another aspect, the present invention consists of coating talc with polyethers and functionalized polyethers to reduce film additive adsorption onto the talc. The general structural formula is:



where n is the number of repeating units (molecular weight), x is zero or an integer, R is an alkyl group, O is oxygen, C is carbon, H is hydrogen, and R_1 is a functional group which may be, without limitation, an alkyl carboxylate, an alkyl amine, an alkyl amide, an alkyl thiol, an alkyl sulfate, an alkyl sulfonate, an alkyl phosphate or an alkyl phosphonate and the like.

Polyethers and functionalized polyethers that are useful for the surface treatment of talc may be selected from the group consisting of poly(ethylene glycol), poly(ethylene glycol) Bis-(carboxymethyl) ether, poly(ethylene glycol) dimethyl ether, poly(ethylene glycol-400) distearate, and the like, and functionalized polyethers (alkyl carboxylate, alkyl amine, alkyl amide, alkyl sulfate, alkyl thiol, alkyl sulfonate, alkyl phosphate, alkyl phosphonate) wherein alkyl carboxylate functionality is preferred. There is no limitation on the method used to produce the polyethers and functionalized polyether polymers. The polyethers and functionalized polyethers of the present invention may be manufactured by ionic polymerization or radical polymerization and the like, or by any other process known to produce polyethers and functionalized polyethers.

The molecular weight range of the polyethers and functionalized polyethers is from

about 1000 to about 10,000,000 a.m.u., with a preferred range of from about 10,000 to about 1,000,000 a.m.u. The molecular weight can be determined by GPC.

In a further aspect the present invention pertains to the use of carbon based polymer coatings for surface treating the talc in order to lower the level of additive adsorption. Also included in the definition of carbon based polymers are maleic acid/olefin co-polymers having the general formula:



where n denotes molecular weight and x and y represent the ratio of each monomeric unit in the polymer. Carbon based polymers that are useful for the surface treatment of talc may be selected from the group consisting of functionalized polyolefins: maleic acid/olefin copolymer, maleic acid/styrene copolymer, wherein maleic acid/styrene copolymer is preferred. Also included in the carbon-based polymers group are mineral oils of any boiling point and paraffin waxes of any melting point. The x/y ratio can range from about 100:1 to about 1:100, wherein the preferred range is from about 10:1 to about 1:10. C is carbon, O is oxygen, H is hydrogen and R is a functional group. R may be any group that can form a bond with carbon. This includes, without limitation, alkyl carboxylates, alkyl amines, alkyl amides, alkyl thiols, alkyl sulfates, alkyl sulfonates, alkyl phosphates, and alkyl phosphonates and the like.

The molecular weight of the carbon based polymer may range from about 100 to about 10,000,000 a.m.u., with a preferred range of from about 200 to about 2,000,000 a.m.u.

Any inorganic mineral, such as, talc, calcium carbonate, precipitated calcium carbonate, clay or silica, that is receptive to surface treatment may be coated with the polymers described herein. However, talc is the preferred inorganic mineral. Talcs that are particularly useful are those that are receptive to both surface treatment and that are capable of subsequent use in polyolefin film production. An exemplary, but nonlimiting talc, would typically have an empirical formula of $\text{Mg}_3\text{Si}_4\text{O}_{10}(\text{OH})_2$ and a specific gravity of from about 2.6 to about 2.8. The preferred talc, without other limitations, could have an average particle size of from about 0.1 microns to about 10 microns, wherein the preferred average particle size is from about 0.5 microns to about 5 microns. The talc may be coated with from about 0.01 weight percent to about 10 percent of the polymers described herein, wherein the preferred treatment level for coating is from about 0.25 weight percent to 2 weight percent, based on the weight of the polymer.

All of the polymer coatings described herein may be applied to talc by any convenient dry powder mixing operation. The temperature at which the coating is applied to the talc, ranges from about 0 zero degrees Centigrade (C) to about 500 degrees C, preferably from about 30 degrees C to about 200 degrees C, and more preferably, from about 60 degrees C to about 80 degrees C. The application temperature should be adjusted to higher levels if the specific coating requires melting. Once the talc is coated, an antiblock talc is produced that may be used, by those skilled in the art, just as any other commercially available antiblock. For example, but without limitations, the coated antiblock talc may be added to the film extruder or added as an already compounded masterbatch to the extruder. A compounded masterbatch means the resin and the antiblock are pre-mixed in a compounder before being added to the film extruder.

Polyolefins considered suitable for the present invention may be any polyolefin, which can be clear, crystalline, and capable of forming a self-supported film. Non-limiting examples include crystalline homopolymers of α -olefin with carbon numbers ranging from 2 to 12 or a blend of two or more crystalline copolymers or ethylene-vinylacetate copolymers with other resins. Also, the polyolefin resin can be a high-density polyethylene, low density polyethylene, linear low-density polyethylene, polypropylene, ethylene-propylene copolymers, poly-1-butene, ethylene-vinyl acetate copolymers, etc., and low and medium-density polyethylenes. Additional examples are represented by random or block copolymers of polyethylene, polypropylene poly-*r*-methylpentene-1, and ethylene-propylene, and ethylene-propylene-hexane copolymers. Among them, copolymers of ethylene and propylene and those containing 1 or 2 selected from butene-1, hexane-1, 4-methylpentene-1, and octene-1 (the so-called LLDPE) are particularly suitable.

The method of producing polyolefin resin used in the present invention is not limited. For example, it can be manufactured by ionic polymerization or radical polymerization. Examples of polyolefin resins obtained by ionic polymerization include homopolymers such as polyethylene, polypropylene, polybutene-2, and poly-4-methylpentene and ethylene copolymers obtained by copolymerizing ethylene and α -olefin, α -olefins having from 3 to 18 carbon atoms such as propylene, butene-1, 4-methylpentene-1, hexene-1, octene-1, decene-1, and octadecene-1 are used as α -olefins. These α -olefins can be used individually or as two or more types. Other examples include propylene copolymers such as copolymers of propylene and butene-1. Examples of polyolefin resins obtained by radical polymerization include ethylene alone or ethylene copolymers obtained by copolymerizing ethylene and radical polymerizable monomers. Examples of radical polymerizable monomers include unsaturated carboxylic acids such as acrylic acid, methacrylic acid and maleic acid esters and acid

anhydrides thereof, and vinyl esters such as vinyl acetate. Concrete examples of esters of unsaturated carboxylic acids include ethyl acrylate, methyl methacrylate and glycidyl methacrylate. These radical polymerizable monomers can be used individually or as two or more types.

5

A typical embodiment of the present invention could include:

	From about	To about	
10	0.1% - 1.0%		talc antiblock
	0.02% - 0.5%		process aid
	0.05% - 0.25%		slip agent
	0.01% - 0.5%		antioxidant
	0.01% - 0.25%		scavenger
15	<u>0.1% - 5.0%</u>		<u>siloxane, silane, polyether, carbon based polymer</u>
	99.7% - 92.5%		polyolefin resin

A typical preferred embodiment of the present invention includes:

20	0.5%	talc antiblock
	0.15%	process aid
	0.12%	slip agent
	0.03%	antioxidant
	0.05%	scavenger
25	0.10%	antioxidant
	<u>2.50%</u>	<u>siloxane, silane, polyether, carbon based polymer</u>
	96.55%	polyolefin resin

All percentages are based on total weight percent.

30

TEST METHODS AND PROCEDURES

Equipment:

- 35 1. Extruders. The following extruders were used to measure the effect of antiblocks on process aid (PA) performance.

- 5
- a. Brabender Single Screw Tape Die Extruder
 - b. ZSK co-rotating low intensity twin screw extruder
 - c. Lestritz low intensity counter-rotating twin screw extruder
 - d. Welex Extruder
2. Henshal Mixer. Used for mixing the siloxane, or silane, or polyether, or carbon based polymer and antiblock compounds.
- 10 3. Killion Blown Film Line. This is a 1^{1/4} inch extruder with a L/D ratio of 30:1 and 2^{1/2} inch die with a 12mm die gap. The temperature profile of the extruder and the blown film line were 177°C, 93°C, 193°C, 204°C, 204°C, 204°C, 204°C, 204°C, 204°C, and 204°C with a melt temperature of 200-208°C. Output was about 9 lbs/hr. with a sheer rate of 500 sec⁻¹. Die pressure and melt fracture reduction were monitored every 15 minutes for
- 15 two hours.

Definition of Terms:

20 Extrusion – fundamental processing operation in which a material is forced through a metal forming die, followed by cooling or chemical hardening (see Hawley's Condensed Chemical Dictionary, 12th Edition 1993, page 505).

25 Die – a device having a specific shape or design in which it imparts to plastic by passing the material through it (extrusion). Die extruders are used to measure the effect of anti-blocks on process aid (PA) performance.

Tape Die Extrusion – extrusion procedure for measuring process aid demand based on the amount of process aid required to reduce die pressure and eliminate melt fracture.

30 Antiblock – materials that roughen the surface of plastic films to reduce their tendency to stick together. These materials may include synthetic silica, diatomaceous earth (DE), and talc.

35 Clarity Antiblock – a type of antiblock that is added when compounding chemicals, to reduce opacity and to improve the clarity of the polymer film.

Process Aid (PA)– provides lubrication or slip at the die during film extrusion which improves film quality by elimination of melt fracture. Process aids are evaluated on pressure reduction (less PA absorbed) and elimination of melt fracture (percent melt fracture).

5

Die Pressure – Pressure at the die. Die pressure reduction is how well the process aid is performing, meaning that the process aid is not absorbed by the talc and hence, is available to reduce die pressure.

10

Melt Fracture – a measure of film surface uniformity. The objective is complete elimination of melt fracture. Melt fracture is monitored as a function of time at a given PA dosage and measured in a rate conditioning test.

15

Rate of Conditioning – Technique used by film manufacturers to determine process aid (PA) performance and to determine the effect of a given antiblock on PA effectiveness. This is done using tape die extrusion and monitoring die pressure and percent melt fracture over a period of time.

20

ABT-G – an ABT 2500® talc coated with an amine functionalized siloxane (Genese Polymers, GP-4).

Functional Groups – The arrangements of atoms and groups of atoms that occur repeatedly in an organic substance.

25

Blown Film Test – Type of extrusion that after the polymer compounded is formed to its desired thickness by air being blown through a cylindrical die.

30

Antioxidant – An organic compound added to plastics to retard oxidation, deterioration, rancidity, and gum formation (see Hawley's Condensed Chemical Dictionary, 12th Edition 1993, page 90).

35

Feldspar – General name for a group of sodium, potassium, calcium, and barium aluminum silicates (see Hawley's Condensed Chemical Dictionary, 12th Edition 1993, page 509).

Diatomaceous earth (DE) – Soft, bulky, solid material (88% silica) composed of small

5 Paraffin (alkane) – a class of aliphatic hydrocarbons characterized by a straight or branched carbon chain (C_nH_{2n+2}) (see Hawley's Condensed Chemical Dictionary, 12th Edition 1993, page 871).

10

15

In Example 1 and Example 2, the antiblock is compounded with a linear low density polyethylene (PE) in a ZSK co-rotating low intensity twin screw extruder at 30 percent loading levels. In a separate batch process the process aid is compounded with the PE at a 10 percent loading level. Process aid dosage was varied from zero parts per million to 1400ppm in 200ppm increments. The samples were extruded at a constant rate (20g/min) for one hour, at each increment, with die pressure and tape melt fracture being monitored throughout. VITON® Free-Flow SAX 7431 (Genese Polymers) process aid was used in Example 1 and replaced with Dynamar™ FX-5920 (Dynamar Products – 3M Center, St. Paul, Minnesota 55144) process aid in Example 2.

35

ABT® 2500 talc, ABT® 2500 talc treated with an amine functionalized siloxane (ABT-G), B4 (Viton Products – Viton Business Center, P.O. Box 306, Elkton, Maryland 21922) clarity antiblock, B4 treated with an amine functionalized siloxane, Celite 238 D.E. (Celite Products – Solon, Ohio), synthetic silica, and MICROBLOC® talc. The treated antiblocks are prepared by dry coating in a Henschel mixer for ten minutes, at 70°C, with a siloxane polymer, at a coating level of one percent by dry weight of talc. The coating consisted of an amine functionalized siloxane (Genese Polymers – GP-4).

In addition to analyzing the three talc samples described above, a clarity antiblock consisting of 50 percent by volume MP 10-52 and 50 percent by volume Feldspar, a GP-4 treated clarity antiblock, ABT 2500® talc, MICROBLOC® talc, diatomaceous earth (Celite Superfloss 238) and synthetic silica (Crosfield 705 – Crosfield Products – 101 Ingalls Avenue, Joliet, Illinois 60435) were also examined.

Table 1 VITON® FLUOROELASTOMER PROCESS AID DOSAGE		
Anti-Block	Process Aid (parts per million)	Percent Melt Fracture
ABT® 2500 talc	1200	40
ABT-G siloxane coated talc	400	10
B4 clarity antiblock	1000	25
B4 siloxane coated	400	15
Celite 238 D.E.	800	40
Synthetic Silica ^a	600	2
MICROBLOC® talc	1000	20

^a 2000 parts per million synthetic silica

Lower process aid dosages were required to reduce melt fracture when the talc and clarity antiblocks were treated with a siloxane coating.

Example 2. Talc and synthetic silica as antiblocks

In this example, the process aid used in Example 1 was replaced Dynamar™ FX-5920 process aid. ABT 2500® talc (uncoated and coated with a siloxane) was compared with a synthetic silica and a commercially available antiblock for process aid demand. Table 2 shows

the amount of process aid required to reduce melt fracture.

Table 2 DYNAMAR™ FLUOROELASTOMER PROCESS AID DOSAGE		
Anti-Block	Process Aid (parts per million)	Percent Melt Fracture
ABT® 2500 talc	1200	50
ABT-G siloxane coated talc	1000	20
Synthetic Silica ^a	1200	80
MICROBLOC® talc	1200	65

^a 2000 parts per million synthetic silica

- 5 The siloxane coated talc required lower amounts of process aid to reduce melt fracture than did the other antiblocks.

Section II. Antiblock coatings and their effect on process aid performance

- 10 In Example 3, melt fracture and die pressure data of ABT® 2500 talc, ABT-G siloxane coated talc, and diatomaceous earth (DE) were compared. In Example 4, commercially available talc antiblocks were evaluated for process aid performance and compared with those in Example
3. Example 5 through Example 7, investigate alternative coatings for an improved antiblock.

- 15 The antiblocks were compounded with blends containing polyethylene resin, 5,000ppm antiblock, 1,000ppm VITON® Free Flow SAX – 7431 PA, 1,200ppm Croda ER erucamide slip agent, 300ppm Irganox® 1010 antioxidant, 500ppm J.T. Baker zinc stearate scavenger, and 1,000ppm Irgafos® 168 antioxidant were compounded on the Lestritz low intensity counter-rotating twin screw extruder. Extruder conditions consisted of temperature zones of 165°C,
- 20 175°C, 190°C, 200, and 204°C. A screw speed at 150rpm with one port and one hopper. The extender screws were 34mm in diameter with a L/D ratio of 22:1.

Example 3. Melt fracture and die pressure performance of antiblocks

25

Die pressure and percent melt fracture were determined for ABT® 2500 talc, ABT-G siloxane coated talc, and DE antiblocks, using tape die extrusions. Percent melt fracture and die pressure data for these antiblocks throughout a one hour tape extrusion are listed below.

Table 3 RATE OF CONDITIONING Benchmark Antiblocks						
	ABT® 2500 talc		ABT-G siloxane coated talc		Diatomaceous Earth	
Time (min)	% Melt Fracture	Die Pressure (psi)	% Melt Fracture	Die Pressure (psi)	% Melt Fracture	Die Pressure (psi)
0	100	3110	10	3100	100	3100
10	100	3100	100	3100	100	3040
20	100	3100	100	3100	55	2740
30	95	3100	85	2990	20	2640
40	90	3070	60	2830	10	2540
50	80	2870	50	2790	0	2480
60	65	2880	35	2760		

A decrease in melt fracture of 30 percentage points and a die pressure reduction of 120psi was seen when ABT® 2500 talc was treated with an amine functionalized siloxane (ABT-G).

Example 4. – Commercial Talc Antiblocks

In this example, commercially available MICROBLOC® talc, POLYBLOC™ talc, and MICROTUFF® AG 101 talc antiblocks were compared with the antiblocks used in Example 3. Measurements were taken throughout a one hour tape extrusion. Percent melt fracture is found in Table 4 and die pressure data in Table 5.

Table 4**RATE OF CONDITIONING/COMMERCIAL TALCS****Percent Melt Fracture**

Time (min)	ABT® 2500 talc	ABT-G siloxane coated talc	D. E.	MICROBLOC® Talc	POLYBLOC™ Talc	MICROTUFF® AG 101 Talc
0	100	100	100	100	100	100
10	100	100	100	100	100	100
20	100	100	55	96	95	100
30	95	85	20	95	85	85
40	90	60	10	75	75	65
50	80	50	0	50	55	55
60	65	35		40	40	45

MICROBLOC®, POLYBLOC™, and MICROTUFF® are trademarks of and are commercially available through Minerals Technologies Inc. – The Chrysler Building, 405 Lexington Avenue, New York, New York 10174.

5

The siloxane coated talc (ABT-G) had a lower percentage melt fracture than the commercially available talc antiblocks.

Table 5**RATE OF CONDITIONING/COMMERCIAL TALCS****Die Pressure (psi)**

Time (min)	ABT® 2500 talc	ABT-G siloxane coated talc	D. E.	MICROBLOC® Talc	POLYBLOC™ Talc	MICROTUFF® AG 101 Talc
0	3110	3100	3100	3110	3140	3120
10	3100	3100	3040	3110	3130	3120
20	3100	3100	2740	3100	3130	3120
30	3100	2990	2640	3090	3030	3020
40	3070	2830	2540	2930	2950	2950
50	2970	2790	2480	2860	2840	2850
60	2880	2760		2790	2780	2790

The siloxane coated talc (ABT-G) had lower die pressure than the commercially available talc antiblocks.

Example 5. - Siloxane Coated Talc Antiblocks

ABT 2500® talc in addition to being coated with the amine functional silicone fluid (ABT-G)/(Genese Polymers, GP-4), was coated with an aminomodified propyltrimethoxy silane (OSI, Silquest® A-1130 silane), and a bis-(trimethoxysilylpropyl) amine (OSI, Silquest® A-1170 silane). Tape die extrusions were used to determine melt fracture and die pressure.

Tape die extrusion results are listed in Table 6 and Table 7.

Table 6						
RATE OF CONDITIONING						
Percent Melt Fracture						
Time	ABT®	ABT-G	D. E.	SILQUEST®	SILQUEST®	Polyacrylate
(min)	2500 talc	coated talc		A-1130 coated talc	A-1170 coated talc	coated talc
0	100	100	100	100	100	100
10	100	100	100	100	100	100
20	100	100	55	98	95	95
30	95	85	20	95	85	90
40	90	60	10	85	60	65
50	80	50	0	75	45	45
60	65	35		65	30	35

SILQUEST®A-1170 and the polyacrylate coated products show lower melt fracture than the uncoated talc and performs similarly to siloxane coated (ABT-G) talc.

Table 7						
RATE OF CONDITIONING						
Die Pressure (psi)						
Time (min)	ABT® 2500	ABT-G	D. E.	SILQUEST® A-1130	SILQUEST® A-1170	Polyacrylate
0	3110	3100	3100	3110	3140	3110
10	3100	3100	3040	3110	3130	3100
20	3100	3100	2740	3110	3120	3100
30	3100	2990	2640	3080	2980	3080
40	3070	2830	2540	3060	2800	2940
50	2970	2790	2480	2970	2770	2790
60	2880	2760		2870	2710	2750

ABT® 2500 talc coated with SILQUEST® A-1170 and the polyacrylate show reduced die pressures when compared with the uncoated ABT® 2500 talc.

Example 6. – Polyether Coated Talc Antiblocks

5

This example shows the effect of polyethers as coatings for low PA talc antiblocks. ABT® 2500 talc was coated with polyethylene glycol (PEG), a PEG product functionalized with polar carboxylate groups, and a PEG product functionalized with less polar stearate groups. Melt fracture data is found in Table 8 and die pressure results are found in Table 9.

Table 8						
RATE OF CONDITIONING/POLYETHER COATINGS						
Percent Melt Fracture						
Time (min)	ABT® 2500 talc	ABT-G siloxane coated talc	D. E.	Polyethylene Glycol (PEG) 200 coated talc	PEG Carboxy coated talc	PEG Distearate coated talc
0	100	100	100	100	100	100
10	100	100	100	100	100	100
20	100	100	55	100	100	95
30	95	85	20	95	95	70
40	90	60	10	75	75	40
50	80	50	0	55	55	35
60	65	35		45	30	25

All three ether coated talcs had lower melt fractures than the uncoated ABT® 2500 talc.

Table 9						
RATE OF CONDITIONING/POLYETHER COATING						
Die Pressure (psi)						
Time (min)	ABT® 2500 talc	ABT-G siloxane coated talc	D. E.	Polyethylene Glycol (PEG) 200 coated talc	PEG Carboxy coated talc	PEG Distearate
0	3110	3100	3100	3100	3120	3140
10	3100	3100	3040	3100	3110	3100
20	3100	3100	2740	3090	3080	3090
30	3100	2990	2640	3070	3030	2930
40	3070	2830	2540	2930	2840	2820
50	2970	2790	2480	2840	2770	2760
60	2880	2760		2750	2740	2670

5 All three ether coated talcs had lower die pressures than the uncoated talc.

Example 7. – Carbon Based Polymer Coated Talc Antiblocks

Functionalized polyolefins and paraffins were examined for melt fracture and die pressure with respect to PA demand. The polyolefins included a maleic acid/olefin copolymer and a maleic acid/ styrene copolymer. A low molecular weight paraffin (mineral oil) and a high molecular weight paraffin (paraffin wax) were also evaluated as talc coating. The molecular weight of the paraffin is from about 80 to about 1400 a.m.u., wherein the preferred molecular weight is from about 200 to about 600 a.m.u. Melt fracture results are in Table 10 and die pressure results in Table 11.

Table 10							
RATE OF CONDITIONING							
Percent Melt Fracture							
Time (min)	ABT® 2500 Talc	ABT-G	D. E.	Maleic- co-olefin	Maleic- styrene	Mineral Oil	Paraffin Wax
0	100	100	100	100	100	100	100
10	100	100	100	100	100	100	100
20	100	100	55	100	100	100	90
30	95	85	20	90	90	90	60
40	90	60	10	40	75	65	35
50	80	50	0	35	40	50	20
60	65	35		30	20	40	15

All four of the talc samples coated with a carbon based polymer had lower melt fracture than the uncoated ABT® 2500 talc. Paraffin wax showed a melt fracture of 15 percent after one
5 hour.

Table 11							
RATE OF CONDITIONING							
Die Pressure (psi)							
Time (min)	ABT® 2500 Talc	ABT-G	D. E.	Maleic-co- olefin	Maleic- styrene	Mineral Oil	Paraffin Wax
0	3110	3100	3100	3100	3080	3110	3120
10	3100	3100	3040	3100	3080	3100	3100
20	3100	3100	2740	3100	3070	3080	3010
30	3100	2990	2640	3030	3030	3020	2860
40	3070	2830	2540	2820	2900	2840	2760
50	2970	2790	2480	2720	2750	2780	2710
60	2880	2760		2700	2680	2750	2660

All of the carbon based polymers had higher die pressure reductions than the uncoated ABT® 2500 talc.

CLAIMS

1. A method of producing an antiblock agent comprising surface treating particulate inorganic minerals with a functionalised siloxane, a polyether, a functionalised polyether, or a carbon based polymer.
5
 2. The method of Claim 1 wherein the inorganic mineral is selected from a group consisting of talc, calcium carbonate, clay and silica.
 - 10 3. The method of any of the preceding claims wherein the functionalised siloxane is a functionalised alkyl polydimethyl methyl siloxane.
 4. The method of Claim 3 in which the functionalised alkyl polydimethylsiloxane is functionalised with one or more of carboxylic, amino, amido, thio, sulpho or phospho groups.
15
-
5. The method of Claim 1 or Claim 2 wherein the siloxane is selected from the group consisting of octyltriethoxysiloxane, triamino functional siloxane, Bis-(gamma-trimethoxysilylpropyl) amine.
20
 6. The method of Claim 1 or Claim 2 wherein the functionalised siloxane has a structural formula of $[\text{Si}(\text{CH}_3)(\text{R})-\text{O}-\text{Si}(\text{CH}_3)(\text{R})-\text{O}]_n$ and wherein the molecular weight is from 100 to 100,000 a.m.u.
 - 25 7. The method of Claim 1 or Claim 2 wherein the siloxane has a structural formula of SiR_4 , where R is a functionalised alkyl group or functionalised alkoxy group.
 8. The method of Claim 1 or Claim 2 wherein the polyether is selected from the group consisting of poly(ethylene glycol), poly (ethylene glycol) Bis-(carboxymethyl) ether, poly (ethylene glycol) dimethyl ether, poly (ethylene glycol-400) distearate, and the like, and the functionalised polyether is selected from the group consisting of polyethylene glycol and other functionalised polyethers such as, for example, alkyl carboxylate, alkyl amine, alkyl amide, alkyl sulphate, alkyl thiol, alkyl sulphonate, alkyl phosphate, alkyl phosphonate, wherein alkyl carboxylate is preferred.
30
 - 35 9. The method of Claim 8 wherein the polyether is polyethylene glycol (PEG) and the

functionalised polyether is alkyl carboxylate functionalised PEG.

10. The method of Claim 8 or Claim 9 wherein the polyether and functionalised polyether have a general structural formula of $H-(OCHR(CH_2)_xCHR_1)_n-OH$ and wherein the molecular weight is from 100 to 100,000 a.m.u.
11. The method of Claim 1 or Claim 2 wherein the carbon based polymer is selected from the group consisting of functionalised polyolefins maleic acid/olefin copolymer, maleic acid/styrene copolymer.
12. The method of Claim 11 wherein the carbon based polymer is maleic acid/styrene copolymer.
13. The method of Claim 11 or Claim 12 wherein the carbon based polymer has a general structural formula of:



- and wherein the molecular weight is from 1,000 to 10,000,000 a.m.u. wherein x and y represent the ratio of each monomeric unit in the polymer
14. A method according to any of the preceding claims in which the inorganic material is talc.
15. The method of any of the Claims 1,2 and 11 to 14 wherein the inorganic material is treated with from 0.1 to 10 percent, based on weight of inorganic mineral, of the carbon based polymer.
16. A composition comprising an inorganic mineral core component selected from the group consisting of talc, calcium carbonate, clay and silica and a surface treating component selected from the group consisting of functionalised siloxane, a polyether, a functionalised polyether, and a carbon based polymer.
17. The use of a composition according to Claim 16 as an antiblock.

18. A polyolefin containing a composition according to Claim 16.

19. A polyolefin film according to Claim 18.

5

10

15

20

25

30

35

INTERNATIONAL SEARCH REPORT

International Application No
PCT/IB 99/02099

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C08K9/08 C09C3/10 C08L23/02 C08J5/18

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08K C09C C08L C08J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 629 749 A (KITCHEL FRANK T ET AL) 16 December 1986 (1986-12-16)	1,2, 8-10, 16-19
X	claims 1-5 DATABASE WPI Section Ch, Week 199846 Derwent Publications Ltd., London, GB; Class A60, AN 1998-537682 XP002137886 & JP 10 237348 A (NIPPON SHOKUBAI CO LTD), 8 September 1998 (1998-09-08) abstract	1,2
X	WO 96 22326 A (GRACE GMBH) 25 July 1996 (1996-07-25) claims 1-17	1,2,16, 17

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

A document member of the same patent family

Date of the actual completion of the international search

17 May 2000

Date of mailing of the international search report

26/05/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Siemens, T

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/IB 99/02099

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4629749	A	16-12-1986	US 4784822 A	15-11-1988
JP 10237348	A	08-09-1998	NONE	
WO 9622326	A	25-07-1996	DE 19502629 A	25-07-1996
			AU 693642 B	02-07-1998
			AU 4536896 A	07-08-1996
			BR 9607569 A	21-07-1998
			CA 2209566 A	25-07-1996
			DE 69600523 D	17-09-1998
			DE 69600523 T	06-05-1999
			EP 0804502 A	05-11-1997
			JP 10512605 T	02-12-1998
			US 5609679 A	11-03-1997

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.